



Composition: ·Inner tube: thermoplast.
·Reinforcement: one or two braids of synthetic fiber plus one special braid of synthetic fiber.
·Cover: red polyurethane.

Working temperature: From -40° C to +60° C.

Part n°	DN	Ø in	Ø out	Working Pressure (bar)	Working pressure (psi)	Burst pressure (bar)	Burst pressure (psi)	Bending radius (mm)	Weight (kg/m)	LONGITUD (M)
MTREC2501280	3/4"	19,6	30,4	250	3.600	625	9.000	120	0,581	80
MEC25012	3/4"	19,6	30,4	250	3.600	625	9.000	120	0,438	120
MTREC25012	3/4"	19,6	30,4	250	3.600	625	9.000	120	0,438	120
MEC25012160	3/4"	19,6	30,4	250	3.600	625	9.000	120	0,438	160
MTREC25012160	3/4"	19,6	30,4	250	3.600	625	9.000	120	0,438	160
MTREC2501680	1"	25,6	36,8	250	3.600	625	9.000	155	0,581	80
MEC25016	1"	25,6	36,8	250	3.600	625	9.000	155	0,581	120
MTREC25016	1"	25,6	36,8	250	3.600	625	9.000	155	0,581	120
MEC25016160	1"	25,6	36,8	250	3.600	625	9.000	155	0,581	160
MTREC25016160	1"	25,6	36,8	250	3.600	625	9.000	155	0,581	160
MTREC2502080	1" 1/4	32,4	46	250	3.600	625	9.000	240	0,808	80
MTREC25020	1" 1/4	32,4	46	250	3.600	625	9.000	240	0,808	120
MEC25020160	1" 1/4	32,4	46	250	3.600	625	9.000	240	0,808	160
MTREC25020160	1" 1/4	32,4	46	250	3.600	625	9.000	240	0,808	160